

AD-A247 449



①

TECHNICAL REPORT


*"A Method to Determine Moisture Profiles
From Total Moisture Weight-Gain Data in
Polymeric Composites"*

By

Y. Jack Weitsman

Prepared for: Office of Naval Research
Arlington, Virginia

Mechanics Division
Engineering Sciences Directorate
Contract N00014-90-J-1556



Report ESM91-1.0-MECH
September 1991

92-05987



Engineering Science and Mechanics
THE UNIVERSITY OF TENNESSEE
Knoxville, TN 37996-2030



DISTRIBUTION STATEMENT A

Approved for public release;
Distribution Unlimited

92 3 05 056

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION unclassified		1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY		3. DISTRIBUTION/AVAILABILITY OF REPORT unlimited	
4. DECLASSIFICATION/DOWNGRADING SCHEDULE		5. MONITORING ORGANIZATION REPORT NUMBER(S)	
6. PERFORMING ORGANIZATION REPORT NUMBER(S) ESM 01-1.0 MECH		7a. NAME OF MONITORING ORGANIZATION ONR	
7a. NAME OF PERFORMING ORGANIZATION Engineering Science & Mechanics University of Tennessee at Knoxville		7b. ADDRESS (City, State and ZIP Code) Mechanics Division Office of Naval Research, Code 432 800 Quincy Ave., Arlington VA 22217	
8. ADDRESS (City, State and ZIP Code) 07 Perkins Hall Knoxville TN 37996-2030		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-90-J-1556 (ONR Contract #)	
10. NAME OF FUNDING/SPONSORING ORGANIZATION NR		11. ADDRESS (City, State and ZIP Code)	
12. TITLE (Include Security Classification) A Method to Determine Moisture Profiles from Total Moisture Weight-Gain in Polymeric Composites		13. SOURCE OF FUNDING NOS.	
14. PERSONAL AUTHOR(S) Dr. Y. Jack Weitsman		15. TYPE OF REPORT Technical	
16. TYPE OF REPORT Technical		17. 13b. TIME COVERED FROM 10-1-90 TO 9-30-91	
18. 14. DATE OF REPORT (Yr., Mo., Day) 9-12-91		19. 15. PAGE COUNT 17	
20. SUPPLEMENTARY NOTATION			
21. COSATI CODES		22. 18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB. GR.	
23. ABSTRACT (Continue on reverse if necessary and identify by block number)			
This article presents a numerical approximation scheme, based upon the method of moments, to evaluate moisture distributions within a composite plate from data on total moisture weight-gain. Although it is assumed that the diffusion process remains linear, the scheme applies to moisture uptake data which depart from classical predictions. Two examples are provided to demonstrate the validity of the scheme.			
24. DISTRIBUTION/AVAILABILITY OF ABSTRACT CLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS APT. <input type="checkbox"/> DTIC USERS <input type="checkbox"/>		25. 21. ABSTRACT SECURITY CLASSIFICATION unclassified	
26. NAME OF RESPONSIBLE INDIVIDUAL Mr. Yapa Rajapakse		27. 22b. TELEPHONE NUMBER (Include Area Code) 703 696 0934	
28. 22c. OFFICE SYMBOL			

A METHOD TO DETERMINE MOISTURE PROFILES FROM TOTAL MOISTURE WEIGHT-GAIN DATA IN POLYMERIC COMPOSITES

By

Y. Jack Weitsman
The University of Tennessee at Knoxville

Abstract

This article presents a numerical approximation scheme, based upon the method of moments, to evaluate moisture distributions within a composite plate from data on total moisture weight-gain. Although it is assumed that the diffusion process remains linear, the scheme applies to moisture uptake data which depart from classical predictions. Two examples are provided to demonstrate the validity of the scheme.

1. INTRODUCTION

The most commonly utilized technique to record moisture uptake in polymeric composites, and materials in general, is to expose them to an ambient environment and record weight gain with time. However, for most engineering purposes it is important to know the spatial distributions of moisture rather than the integrated values which correspond to weight gains. Several experimental techniques were employed to record moisture distributions⁽¹⁾⁽²⁾ but these are rather cumbersome, to say the least.

When moisture weight-gain data under exposure to constant ambient conditions follow the values predicted by classical diffusion theory, as shown in Fig. 1, there is good reason to believe that the moisture distributions can be "back tracked" in accordance with well known classical results⁽³⁾. It may be noted that the computations of these distributions are somewhat tedious and that the scheme proposed in the present article appears to be more efficient. Nevertheless, for $M(t)$ which agrees with Fig. 1, the determination of spatial distributions follow well established expressions.

In many circumstances weight gain data deviate rather significantly from the classical predictions shown in Fig. 1. These departures were studied extensively, mainly by polymer scientists, and attributed to a variety of causes and mechanisms. One plausible interpretation attributed those departures to the time dependent configurational rearrangements within the polymer chains, akin to viscoelastic mechanical response (see ref. (4) for a listing of some of these works). According to this interpretation, the chemical potentials of the polymer and the surroundings do not equilibrate instantaneously even under constant ambient conditions. The gradual approach to equilibrium can be expressed by a time-dependent boundary condition within the context of an otherwise linear ("classical") diffusion boundary value problem. Since the boundary condition is generally unknown, it is impossible to "back track" moisture distributions from weight-gain data using textbook solutions. The scheme developed in this article accomplishes this task. However, it should be noted that the precision of the predicted moisture distributions cannot exceed accuracy of the weight-gain data.

2. ANALYSIS

Consider a "classical," one dimensional diffusion process which is governed by the field equation

$$\frac{\partial c}{\partial t} = D \frac{\partial^2 c}{\partial x^2} \quad t > 0, \quad -L \leq x \leq L \quad (1)$$

where c is the concentration of the solvent (water) in, say, percent weight-gain, D the diffusion coefficient in $m^2/sec.$, t denotes time and x is distance across a plate of thickness $2L$. Assuming an initially dry plate, we have

$$c(x,0) = 0 \quad -L < x < L. \quad (2)$$

The boundary conditions are taken to be

$$c(\pm L, t) = f(t) \quad (3)$$

where $f(t)$ reflects the time-dependent response of the polymeric component within the plate. This time-dependence is assumed to occur even under constant ambient conditions, accounting for total weight gains that depart from predictions based upon $f(t) = \text{constant}$.

While most experimental data give total weight gain, namely

$$M(t) = \int_{-L}^L c(x,t) dx \quad \text{the detailed distribution, } c(x,t), \text{ is of higher relevance for computations of residual hygro-thermal stresses in composite laminates.}$$

The following approximate scheme enables us to unravel the information contained in $M(t)$ to obtain $c(x,t)$. The approach extends the "method of moments" developed for unbounded regions⁽⁵⁾.

The formulation presented in equations (1)-(3) gives $c(x,t) = c(-x,t)$. This evenness in x suggests the construction of the even moments defined by

$$M_{(2p)}(t) = \int_{-L}^L x^{2p} c(x,t) dx \quad (4)$$

For future use define the k -fold time integral of $M(t)$

Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

$$I_{(k)}(t) = \int_0^{\tau_{k-1}} \int_0^{\tau_{k-2}} \dots \int_0^{\tau_2} \int_0^{\tau_1} M(\tau) d\tau d\tau_1 \dots d\tau_{k-1} \quad (5)$$

and the k -fold time integral of boundary condition multiplied by $2L$

$$J_{(k)}(t) = 2L \int_0^{\tau_{k-1}} \int_0^{\tau_{k-2}} \dots \int_0^{\tau_2} \int_0^{\tau_1} c(L, \tau) d\tau d\tau_1 \dots d\tau_{k-1} \quad (6)$$

Note that $M_{(0)}(t) = I_{(0)}(t) = M(t)$ and $J_{(0)}(t) = 2LC(L, t)$. Furthermore, for $c(\pm L, t) = c_L = \text{constant}$ we have $2Lc_L = M_\infty$ whereby, for time-independent boundary condition, we have

$$J_{(k)}(t) = M_\infty t^k/k!$$

The method of moments derives from the fact that integration of equation (1) yields

$$\begin{aligned} \int_{-L}^L \frac{\partial c}{\partial t} dx &= \frac{\partial}{\partial t} \int_{-L}^L c(x, t) dx = \dot{M}(t) = \dot{M}_{(0)}(t) = \dot{I}_{(0)}(t) \\ &= D \int_{-L}^L \frac{\partial^2 c}{\partial x^2} dx = 2D \left. \frac{\partial c(x, t)}{\partial x} \right|_{x=L} \end{aligned} \quad (7)$$

Similarly

$$\begin{aligned} \dot{M}_{(2p)}(t) &= D \int_{-L}^L x^{2p} \frac{\partial^2 c}{\partial x^2} dx \\ &= D \left\{ x^{2p} \frac{\partial c}{\partial x} \Big|_{-L}^L - 2p \int_{-L}^L x^{2p-1} \frac{\partial c}{\partial x} dx \right\} \end{aligned}$$

$$\begin{aligned}
&= 2 DL^{2p} \frac{\partial c(x,t)}{\partial x} \Big|_{x=L} - 2p \cdot 2 DL^{2p-1} c(L,t) \\
&+ 2p (2p-1) D \int_{-L}^L x^{2(p-1)} c(x,t) dx \\
&= L^{2p} \dot{I}_{(0)}(t) - 2pDL^{2(p-1)} J_{(0)}(t) + 2p(2p-1)DM_{2(p-1)}(t) \quad (8)
\end{aligned}$$

Integration with respect to t and employment of mathematical induction yield

$$M_{(2p)}(t) = L^{2p} I_{(0)}(t) + \sum_{k=1}^p \frac{(2p)!}{(2p-2k)!} D^k L^{2(p-k)} \left[I_{(k)}(t) - \frac{J_{(k)}(t)}{2(p-k)+1} \right] \quad (9)$$

Note that equation (9) involves the weight-gain data $M(t)$ and their time integrals, a procedure which is much less susceptible to errors than data differentiation.

At this stage it is expedient to introduce the non-dimensional coordinate $\xi = x/L$, with a corresponding distribution $\hat{c}(\xi, t)$. Consequently, we have

$$\widehat{M}_{(2p)}(t) = \int_{-1}^1 \xi^{2p} \hat{c}(\xi, t) d\xi = M_{(2p)}(t) / L^{2p+1} \quad (10)$$

Expand $\hat{c}(\xi, t)$ in a series of even-order Legendre polynomials $P_{2j}(\xi)$

$$\hat{c}(\xi, t) = \sum_{j=0}^k a_{2j}(t) H(t) P_{2j}(\xi) \quad -1 \leq \xi \leq 1 \quad (11)$$

where $a_{2j}(t)$ are the yet unknown coefficients and $H(t)$ is the Heaviside unit step function.

In view of the orthogonality of the Legendre polynomials we have⁽⁶⁾

$$\int_{-1}^1 \hat{c}(\xi, t) P_{2k}(\xi) d\xi = a_{2k}(t) H(t) \frac{2}{4k+1} \quad (12)$$

Substitution of equation (11) into equation (12) and employment of equation (10), determine $a_{2k}(t)$ in terms of the moments $\widehat{M}_{(2j)}(t)$ $j = 0, 1, \dots, k$ as follows

$$\begin{aligned} \frac{2}{4k+1} a_{2k}(t) = & \frac{(4k-1)!!}{(2k-1)!!(2k)!!} \widehat{M}_{(2k)}(t) - \frac{(4k-3)!!}{(2k-3)!!(2k-2)!!2!!} \widehat{M}_{(2k-2)}(t) \\ & + \frac{(4k-5)!!}{(2k-5)!!(2k-4)!!4!!} \widehat{M}_{(2k-4)}(t) - \dots + (-1)^k \frac{(2k-1)!!}{(2k)!!} \end{aligned} \quad (13)$$

In equation (13) we used the notation $(2q-1)!! = 1 \cdot 3 \cdot 5 \cdot \dots \cdot (2q-1)$ and $(2q)!! = 2 \cdot 4 \cdot 6 \cdot \dots \cdot (2q)$.

For instance (6)

$$2a_0(t) = \widehat{M}_{(0)}(t), \quad \frac{2}{5} a_2(t) = \frac{3}{2} \widehat{M}_{(2)}(t) - \frac{1}{2} \widehat{M}_{(0)}(t),$$

$$\frac{2}{9} a_4(t) = \frac{1}{8} [3 \cdot 5 \widehat{M}_{(4)}(t) - 30 \widehat{M}_{(2)}(t) + 3 \widehat{M}_{(0)}(t)],$$

$$\frac{2}{13} a_6(t) = \frac{1}{16} [2 \cdot 3 \cdot 1 \widehat{M}_{(6)}(t) - 3 \cdot 15 \widehat{M}_{(4)}(t) + 10 \cdot 5 \widehat{M}_{(2)}(t) - 5 \widehat{M}_{(0)}(t)], \text{ etc.}$$

In view of equation (13) it is obvious that the representation (11) suffers from accumulations of truncation errors. These errors are due to the inherent scatter in the data for $M_{(0)}(t)$ as well as computational imprecisions in the numerical integrations included in the higher order moments $M_{(2k)}(t)$, $k=1, \dots, p$. The examples presented in the foregoing section indicate that very good results for $c(x,t)$ can be obtained by taking $k \leq 4$, in which case these truncation errors may not exceed a few percentage points.

3. COMPUTATIONAL RESULTS

Computations were performed for two test cases where, for verification purposes, both $c(x,t)$ and $M(t)$ are known analytically. In both cases we took $L = 1.0$ mm and $D = 5.8 \times 10^{-4}$ mm²/sec., while

case (a) : $c(\pm L, t) = 1.0\%$ (constant)

case (b) : $c(\pm L, t) = 0.8 + 0.2 (1 - e^{-\beta t})$, $\beta = 1/200$.

Expressions for $M(t)$ and $c(x, t)$ are given in Ref. (7). The values of $M(t)$ were employed as simulated data to generate $M_{(2p)}(t)$ according to equation (9) and recreate $c(x, t)$ according to equation (11) by solving for $a_{2j}(t)$ in accordance with equation (13).

Results are shown in Figures 2 and 3. These figures show distributions of $c(x, t)$, employing up to six terms in the series (11), for various times. The numerals accompanying the various curves indicate the number of terms in the series, equation (11), employed in their evaluation. For comparison purposes, the exact distributions $c(x, t)$, which are known for cases (a) and (b), are shown in solid lines. Note that, for the cases under consideration, very good results were obtained by using no more than three or four terms in the series (11). The divergence that is caused by taking additional terms is due to truncation errors.

4. CONCLUDING REMARKS

The computational scheme developed in this work employs total weight-gain data to determine moisture distributions across the thickness of polymeric composite laminates. The scheme is most useful for cases where weight-gain data depart from predictions of classical, linear diffusion theory, when no "textbook" solutions are available to relate total uptake to spatial distributions. It should be noted that the scheme is based upon the premise that linear theory, as expressed in equations (1) and (2), still applies, and that the sole cause for deviation from classical weight-gain is the time-dependent material response which is reflected in equation (3). In a forthcoming work we intend to propose some criteria to examine if moisture uptake data concur with the above premise and devise a method to determine $f(t)$. In addition, it should be noted that the diffusion coefficient D is also generally unknown and must be determined experimentally. It is our intention to address this aspect as well.

Acknowledgements

This work was conducted under Contract N00014-90-J-1556 from the Mechanics Division of the Office of Naval Research (ONR). Dr. Y. Rajapakse of the Mechanics Division, Engineering Sciences Directorate, has been the program manager. The author thanks Mr. Cai for obtaining the numerical results presented in Figs. 2 and 3.

REFERENCES

- (1) R.J. Delasi and R.L. Schulte in G.S. Springer, ed., Environmental Effects on Composites, 2, Technomic, Lancaster, 1984, pp. 144-150.
- (2) W. Althof, National SAMPE Conference, 11 309-322, (1979).
- (3) J. Crank, The Mathematics of Diffusion, 2nd Edition, Oxford, London, 1975, pp. 47-48.
- (4) Y. Weitsman, The J. of Phys. Chem., 94 (2), 961-968 (1990).
- (5) R. Ghez, J.D. Fehribach and G.S. Oehrlein, J. Electrochem. Soc., 132, 961-968 (1985).
- (6) W.D. MacMillan, The Theory of the Potential, Dover, New York, 1958, pp. 333-345.
- (7) J. Crank in Ref. 3, pp. 53-54.




Figure 1

The total weight gain ratio $M(t)/M(\infty)$ vs. $\sqrt{t^*}$ according to Fick's Law, with locations where departures from straight-lines exceed 1%. $t^* = Dt/L^2$.

Moisture Distribution Profile

$C(0)=1, C(1)=0, t=50 \text{ hours}$




Figure 2(a)

FIGURE 2. Moisture distribution profiles $c(x,t)$ vs. distance x computed according to equation (11), with k indicated on each dashed curve. The exact solution is shown by solid line. $C_L=1, L=1, D = 5.8 \times 10^{-4}$, (a) $t = 50$, (b) $t = 100$, (c) $t = 200$, (d) $t = 1000$.

Moisture Distribution Profile

$C_0=1, C_1=0, t=100\text{hours}$




Figure 2(b)

FIGURE 2. Moisture distribution profiles $c(x,t)$ vs. distance x computed according to equation (11), with k indicated on each dashed curve. The exact solution is shown by solid line. $C_L=1, L=1, D = 5.8 \times 10^{-4}$, (a) $t = 50$, (b) $t = 100$, (c) $t = 200$, (d) $t = 1000$.

Moisture Distribution Profile

$C_0=1, C_1=0, t=200\text{hours}$




Figure 2(c)

FIGURE 2. Moisture distribution profiles $c(x,t)$ vs. distance x computed according to equation (11), with k indicated on each dashed curve. The exact solution is shown by solid line.
 $C_L=1, L=1, D = 5.8 \times 10^{-4}$, (a) $t = 50$, (b) $t = 100$, (c) $t = 200$, (d) $t = 1000$.




Figure 2(d)

FIGURE 2. Moisture distribution profiles $c(x,t)$ vs. distance x computed according to equation (11), with k indicated on each dashed curve. The exact solution is shown by solid line.
 $C_L=1, L=1, D = 5.8 \times 10^{-4}$, (a) $t = 50$, (b) $t = 100$, (c) $t = 200$, (d) $t = 1000$.

Moisture Distribution Profile

$C_0=0.8, C_1=0.2, \beta=0.005, t=50\text{hours}$




Figure 3(a)

FIGURE 3: Same as Figure 2, except that $C_L = 0.8 + 0.2[1 - \exp(t/200)]$.

Moisture Distribution Profile

$C_0=0.8, C_1=0.2, \beta=0.005, t=100\text{hours}$




Figure 3(b)

FIGURE 3: Same as Figure 2, except that $C_L = 0.8 + 0.2|1 - \exp(t/200)|$.




Figure 3(c)

FIGURE 3: Same as Figure 2, except that $C_L = 0.8 + 0.2[1 - \exp(t/200)]$.




Figure 3(d)

FIGURE 3: Same as Figure 2, except that $C_L = 0.8 + 0.2[1 - \exp(t/200)]$.